



Chemical  
Resistance

## 96 Well Multiwellplate

Item-No. 400100

	+	o	-
<b>Resistant</b>		Limited resistance	Not resistant
<b>Hydrochloric acid 36 %</b>	+		
<b>Sulfuric acid 40 %</b>	+		
<b>Nitric acid 65 %</b>	+		
<b>Acetic acid &gt; 94 %</b>	+		
<b>Water</b>	+		
<b>Aqueous solution of soap</b>	+		
<b>Saline solution</b>	+		
<b>Sodium hydroxide 50 %</b>	+		

<b>Ammonia (aq. Sol.) 35 %</b>	+
<b>Ethanol, methanol, butanol, isopropanol</b>	+
<b>Acetone, butanone</b>	+
<b>Benzaldehyde</b>	0
<b>Toluene</b>	-
<b>Benzene</b>	-
<b>Chlorinated solvents</b>	-
<b>Pentane, hexane, heptane etc.</b>	-
<b>Petrol ether</b>	-
<b>Norbornene</b>	-
<b>Oleic acid</b>	-

Source: <https://topas.com/tech-center/performance-data/chemical-resistance/>

Sheet subject to change without notice!

**Revision 01: 01.08.2024**

**DISCLAIMER:** The description of a certain product can only be considered as a guidance, because its performance ultimately depends on what the product is used for. Very often performance studies are indispensable.